

Lagging material

BRICQ-LAG 60

This woven lagging material has excellent grip on any kind of belt.

It can withstand high temperatures without melting nor getting cracked or leaving deposits on the rolls unlike rubber materials.



Technical Data

Polyester woven lagging material

- Composition : 100 % Polyester (+ coating)
- Weight : 6 500 g/m²
- Thickness : 8.5 mm
- Width : in stripes of 300 mm
- Minimum winding diameter : 120 mm
- Temperature range : -10°C to +150°C

Coating

- High grip coating on belt side.
- Pre-coated with glue on drum side. Still needs to be coated at time of fitting with one kg of glue per sqm of lagging.
- Recommended glues :
Contact glues such as Pattex or Synta from HENKEL, S.1358 from Dunlop or 1300L from 3M

BRICQ-LAG 60 : Easy to fit

- Full fitting procedure available on request.

BRICQ S.A.S.
D 62 Route d'Orgedeuil
16220 Montbron, France
Tel. +33 5 45 23 91 11
Fax +33 5 45 70 86 26

info@bricq.fr